

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**

EUROPEAN PATENT APPLICATION

Application number: 89306056.6

Int. Cl.<sup>4</sup>: C08L 23/02 , B65D 55/06 ,  
 C09J 7/02 , G09F 3/02

Date of filing: 15.06.89

Priority: 27.06.88 US 212412

Date of publication of application:  
 03.01.90 Bulletin 90/01

Designated Contracting States:  
 CH DE FR GB IT LI

Applicant: MINNESOTA MINING AND  
 MANUFACTURING COMPANY  
 3M Center, P.O. Box 33427  
 St. Paul, Minnesota 55133(US)

Inventor: Rivera, Raymond R. c/o Minnesota  
 Mining and  
 Manufacturing Company 2501 Hudson Road  
 St. Paul Minnesota 55144-1000(US)  
 Inventor: VanVleet, Stephen B. c/o Minnesota  
 Mining and  
 Manufacturing Company 2501 Hudson Road  
 St. Paul Minnesota 55144-1000(US)  
 Inventor: Wilson, Shari J. c/o Minnesota  
 Mining and  
 Manufacturing Company 2501 Hudson Road  
 St. Paul Minnesota 55144-1000(US)

Representative: Baillie, Iain Cameron et al  
 c/o Ladas & Parry Isartorplatz 5  
 D-8000 München 2(DE)

Tamper indicating tape and delaminating film therefore.

The present invention relates to delaminating film and a tamper indicating tape made from same for use with a package to indicate opening of the package.

Delaminating films typically include two or more layers of polymeric materials, bonded together either by heat lamination, by coextrusion, or by means of an adhesive layer. Delamination of these composite films by separation of the various layers from each other provides indication of tampering. However, lamination or coextrusion of multiple polymeric layers increases the material expense of the film and tape and requires complex manufacturing techniques.

The present invention provides a tamper indicating film and tape for use with a package. The tape includes a delaminating film including phase separated polymers. Indicia are applied to opposing major surfaces of the film to indicate different conditions of the tape. The film is adhesively applied to secure container parts together and enclose an opening in the container. When applied, only one of the indicia is perceptible. When the film is internally delaminated, one set of indicia is obscured and the other set of indicia is rendered perceptible.




Fig. 1A

## TAMPER INDICATING TAPE AND DELAMINATING FILM THEREFORE

Technical Field

The present invention relates to delaminating film and a tamper indicating tape made from same for use  
 5 with a package to indicate opening of the package.

Background Art

10 U.S. Patent No. 4,652,473 discloses a pressure-sensitive adhesive tape comprising a backing having two separate layers that delaminates. The outer layer has sufficiently high tensile strength to maintain its integrity when removed from the tape and the inner layer adjacent the adhesive is thin and deformable, so that the outer layer can not be removed from the inner layer without disrupting the adhesive bond of the inner layer to the pressure sensitive adhesive, thus providing tamper indication.

15 U.S. Patent No. 4,630,891 discloses a tamper resistant security film comprising a monolayer of transparent microspheres supported in a thin layer of binder material. A layer of pressure-sensitive adhesive is coated onto the binder material and at least one patterned layer having differential adhesion to the pressure-sensitive adhesive layer and the binder layer such that upon attempted removal of the film from a substrate at elevated temperature, the film splits, with part of the film remaining on the substrate and part  
 20 being removed, thus providing tamper indication.

Japanese Patent Applications Publication No. 81JP-061678 and 81JP-061679 (J57176125A & J57176126A) disclose the extrusion and lamination or coextrusion of a rollable and stretchable thermoplastic resin with a ductile and stretchable thermoplastic resin. The composite is then drawn or stretched monoaxially or biaxially to provide a film which can be delaminated to provide very thin layers of the  
 25 respective component resin films.

Delaminating films, such as described in the above references include two or more layers of polymeric materials, bonded together either by heat lamination, coextrusion or by means of an adhesive layer. Delamination for these composite films is the separation of the various layers from each other to provide tamper indication. However, the lamination or coextrusion of multiple polymeric layers increases the  
 30 material expense of the film and tape and requires complex manufacturing techniques.

Disclosure of the Invention

35 The present invention provides, in part, a light transmissive film derived from a composition comprising 50 to 85 parts by weight of a first copolymer comprising at least one moiety derived from at least one olefinic monomeric unit and 50 to 15 parts by weight of a second copolymer comprising at least one moiety derived from at least one vinyl alcohol monomeric unit and said second copolymer being sufficiently incompatible with said first copolymer such that two phases are formed within said film, one of said phases  
 40 being continuous.

The present invention further provides a tamper indicating tape for securing a first container part to a second container part to enclose an opening in the container. The tamper indicating tape includes a light transmissive monolayer film having opposing first and second major surfaces constructed as described above.

45 The tamper indicating tape also includes first colored indicia printed on the first major surface of the film and second colored indicia printed on the second major surface of said film. The first and second indicia have contrasting colors. Adhesive means are provided for adhering the film to the first and the second container parts with a bond strength greater than the delamination force of the film. The adhesive means is coated on said first major surface of said film opposite the second indicia with a color  
 50 substantially identical with the color of the second indicia so that the second indicia are obscured when viewed against the adhesive means through the second major surface of the film.

When the film delaminates, such as if the tape is attempted to be removed from the container, it becomes opaque so that the first indicia are obscured when viewed through the delaminated film, but the second indicia are perceptible over the delaminated opaque film to indicate separation of the first and

Thus a delaminating film and a tamper indicating tape made therefrom are provided that are effective, easy to use and inexpensive to construct.

#### 5 Brief Description of Drawing

The present invention will be further described with reference to the accompanying drawing wherein like reference numerals refer to like parts in the several views, and wherein:

Figure 1A is a cross sectional view of a tamper indicating tape constructed according to the present invention.

Figure 1B is a cross sectional view of the tamper indicating tape of Figure 1A with the film delaminated.

Figure 2A is a top view of a tamper indicating tape according to this invention.

Figure 2B is a top view of the tamper indicating tape of Figure 2A with the film delaminated.

Figure 3A is a photomicrograph at 610X magnification of a longitudinal cross sectional view of a film for use in a tamper indicating tape constructed according to the present invention.

Figure 3B is a photomicrograph at 610X magnification of a transverse cross sectional view of the film of Figure 3A.

Figure 4 is a perspective view of a rectangular container with tamper indicating tape according to this invention securing container parts together to enclose an opening in the container.

#### Detailed Description

Referring now to the drawing, there is shown in Figures 1A, 1B, 2A, 2B, 3A and 3B a tamper indicating tape according to the present invention generally designated by the reference numeral 10. Tape 10 includes a light transmissive film 12. Film 12 includes a first major surface 18 and a second major surface 20. Film 12 is constructed so that the film delaminates internally (i.e., between the first and second major surfaces) when a predetermined level of peel force is applied to the film. Film 12 is derived from a composition comprising 50 to 85 parts by weight of a first copolymer comprising at least one moiety derived from at least one olefinic monomeric unit and 50 to 15 parts by weight of a second copolymer comprising at least one moiety derived from at least one vinyl alcohol monomeric unit.

In one embodiment of the invention, the first copolymer includes from 0 to 15 parts by weight of monomeric units from a polar copolymerizable monomer substantially free of hydroxy (-OH) groups such as is listed in the following group: acrylic acid, acrylonitrile, bicyclo [2,2,1] hept-2-ene, bis (B-chloroethyl) vinylphosphonate, carbon monoxide, diethyl fumarate, diethyl maleate, ethyl acrylate, methacrylic acid, N-methyl-N-vinylacetamide, styrene, vinyl acetate, vinyl chloride, and vinyl fluoride. Preferably, the polar copolymerizing monomer includes moieties derived from one of the following monomeric units: acrylic acid, methacrylic acid and vinyl acetate.

In one preferred embodiment, the first copolymer comprises at least 90 parts by weight (pbw) propylene monomeric units having between 2 and 4 carbon atoms and in the most preferred embodiment, the first polymer comprises about 97 pbw propylene monomeric units and from about 2.2 pbw to about 2.7 pbw ethylene monomeric units.

In one preferred embodiment of the invention, the second copolymer is a copolymer comprising hydrolyzed ethylene vinyl acetate monomeric units, and in the most preferred embodiment of the invention, the second copolymer is a copolymer comprising ethylene vinyl alcohol monomeric units.

As is shown particularly in Figures 3A and 3B, the second copolymer is sufficiently incompatible with the first copolymer to form two phases within the film. One of said phases 14 is continuous, preferably the phase formed by the first copolymer. The second phase 16, preferably that formed by the second copolymer, forms a multiplicity of inclusions 16 in the film, typically ellipsoidal in shape.

In the most preferred embodiment of the invention described above, shown in Figures 3A and 3B, the film comprises about 75 % pbw of the first copolymer and about 25 % of the second copolymer. The first copolymer comprises about 97 pbw propylene monomeric units and from about 2.2 pbw to about 2.7 pbw ethylene monomeric units. The second copolymer is ethylene vinyl alcohol. The ellipsoidal inclusions 16 formed by the second copolymer have been measured and found to have diameters ranging from approximately 0.8 to 3.3 microns and lengths ranging from approximately 1.6 to 13.1 microns. While not wishing to be bound by any theory, it is believed that the inclusions formed by the second copolymer provide a pattern of weaknesses within the continuous phase of the first copolymer. Thus, the delamination

force of the film 12 is predetermined at a desired level depending on the materials selected and their relative ratios. If the second polymer provides more than 50% pbw of the film, the second copolymer begins to form a continuous phase and the film no longer delaminates.

5 Films produced according to the present invention have unexpectedly high light transmissivity levels and low haze, even though the phase separated morphology due to the incompatibility of the first and second copolymers would be expected to form opaque films. It is believed that the relative size of the inclusions and the closeness of the indices of refractions of the components of the film are such that film has good light transmissive properties.

10 The film of this invention may be produced by any suitable film generating process, but is preferably produced by dry blending the first and second polymers together, air drying the blend at 200° F for 48 hours, then extruding the blend onto a driven chilled roll. Preferably, the film is at least 0.003 inches in thickness. At thicknesses less than 0.003 inches, voids form on the surfaces of the film.

15 First colored indicia 22 are printed on first major surface 18 and second colored indicia 24 are printed on the second major surface 20 of the film. As is shown particularly in Figures 2A and 2B, first indicia 22 indicates one condition of the tape, and second indicia 24 indicates another condition of the tape of this invention. First indicia 22 and second indicia 24 have contrasting colors. For instance, first indicia 22 may be colored blue with second indicia 24 colored red.

20 Means are provided to adhere the film to a first container part 26 and a second container part 28 shown particularly in Figures 1A and 1B. Although not shown, the first and the second container parts, when secured together, enclose an opening in a container. The adhesive means includes first layer of adhesive 30 coated on first major surface 18 of the film opposite the second indicia 24, and second layer of adhesive 32 coated on second major surface 20 of the film. Although any suitable adhesive may be used, such as a heat activated adhesive or a pressure sensitive adhesive, in the preferred embodiment of the invention, the first and second layers of adhesives are pressure sensitive adhesives such as resin tackified synthetic 25 rubber adhesives, and in particular styrene-butadiene rubber, styrene-isoprene-styrene and styrene-butadiene-styrene rubber; and acrylic adhesives and in particular isoctylacrylate-acrylic acid; and tackified natural rubber adhesives. For instance, the pressure sensitive adhesive provided with tape number 373 marketed by the Minnesota Mining and Manufacturing Co. of St. Paul, Minnesota 55133 has been found suitable for use in the tamper indicating tape of this invention.

30 First layer of adhesive 30 bonds to film 12 and to first container part 26 with a bond strength that is greater than the delamination force of the film. Second layer of adhesive 32 bonds to the film 12 and the second container part 28 with a bond strength that is also greater than the delamination force of the film. One of the layers of adhesive may be covered by a removable liner, such as a silicone release liner (not shown) prior to application on first and second container parts 26 and 28. First layer of adhesive 30 is 35 preferably colored with a color substantially identical to the color of second indicia 24 so that the second indicia are obscured against the first layer of adhesive when viewed through second major surface 20 of film 12. Second layer of adhesive 32 is light transmissive and preferably colorless so that first indicia 22 are readily perceptible through film 12 and the second layer of adhesive, as shown in Figure 2A.

40 After tape 10 has been secured to first and the second container parts 26 and 28, any separation of the container parts will result in internal delamination of film 12 at a predetermined level of peel force, as shown in Figure 1B. Upon delamination, the separated portions of the film become opaque due to surface irregularities in the exposed internal surfaces of the film created during the delamination of the film. First indicia 22 are no longer perceptible through second major surface 20 of the film. However, as shown in Figure 2B, second indicia 24 are no longer obscured on the background of the first layer of adhesive, but 45 are now readily perceptible against the white opaque background of the separated film portions. This provides an unambiguous indication of unauthorized access to the contents of the container. If desired, first indicia 22 may include alphanumeric characters forming a message indicative of a sealed condition for the container when tape 10 is applied. Second indicia 24 may also include alpha numeric characters forming a message that the container has been opened. Another feature of this invention is that the separated film 50 portions will not readhere to each other once separated. This provides a further indication of unauthorized access to the interior of a container.

Figure 4 illustrates an embodiment of this invention applied to box or like container 34. A length of the tamper indicating tape 10' with an adhesive layer applied only to the first major surface of the film is adhered to first and second container parts 26 and 28, such as the lid and side panel of the container. 55 Opening the container requires destruction of the tape and thus provides an unambiguous indication of access to the interior of the container.

The following examples and test results are used to further illustrate this invention:

EXAMPLE 1

A blend of 75 pbw of a propylene/ethylene copolymer containing 2.7 pbw ethylene monomeric units of the copolymer (available from Fina Oil and Chemical Company, Houston, Texas) and 25 parts by weight of an ethylene vinyl alcohol copolymer containing 44 mole percent ethylene and being essentially completely hydrolyzed (available from Eval Company of America, Lisle, Illinois) was fed into a 3/4" Haake Extruder having a 25:1 L/D (length/diameter) ratio at a temperature of 430° F and 1200 p.s.i. pressure. The extruder screw used had a 3:1 compression ratio and was run at 70 r.p.m. with the die orifice set at 15 mils. The molten film from the die was cast onto a chilled chrome roll at 50-100° F and at a speed of 25 feet per minute and drawn to form a 3 mil thick film. The film was then tested according to the test methods listed herein and the results are shown in Table I.

TABLE I

TENSILE TESTING			
F-1	F-3	Breakstrength (lbs)	% elongation at break
1.0	2.0	3.4	427
DELAMINATION TEST			
Shiny Side (oz/in)	Matte Side (oz/in)		
7.5	7.5		
LIGHT TRANSMITTANCE			
Before Delamination			
% transmittance (T <sub>2</sub> )	% haze		
88.5	40.2		
After Delamination			
% transmittance (T <sub>2</sub> )	% haze		
81.1	67.5		

EXAMPLES 2-7

These were made in the same way as Example 1, except with different first olefinic copolymer and at different ratios of the copolymers (shown in Table II). The tests were also run in the same way as Example 1 and are shown in Table II.

TABLE II

5	Example	2	3	4	5	6	7
10	First Olefinic Copolymers	K123	K222Z	K222Z	K222Z	K123	PE
15	Ratios (First copolymer/ second copolymer)	80/20	80/20	75/25	85/15	85/15	50/50
20							
25							
30							
35							
40							
45							
50							
55							

BEST AVAILABLE COPY



## TENSILE TESTING

5	F-1	1.1	2.5	2.5	--	--	--
	F-3	.0	5.2	5.2	--	--	--
10	Breakstrength (lbs)	3.5	6.6	6.7	--	--	--
15	% elongation	420	250	240	--	--	--

## DELAMINATION TEST (oz./in)

20	Shiny side	5.5	1.5	4.5	2.0	3.0	>32.0
25	Matte side	7.5	1.8	3.5	8.0	11.3	>16.0

## LIGHT TRANSMITTANCE

30				<u>Before Delamination</u>			
	% transmittance	88.1	--	--	77.6	80	81.6
	(T <sub>2</sub> )						
35	% Haze	37.7	--	--	97.5	98	96
				<u>After Delamination</u>			
40	% transmittance	80	--	--	81.4	84.6	84.1
	(T <sub>2</sub> )						
	% Haze	97.1	--	--	96.2	97.4	90.8

TEST METHODS

50

1. Delamination Test: A 4" (10 cm) piece of Scotch Brand 600 tape was folded to itself with .5" overlap to form a tab. The tape was rolled at about 12"/minutes using a 4.5 pound roller onto a film constructed according to the present invention. An alligator clip was then attached to the tab and attached to the end of a 2 pound Ametek Force Gauge. The tab was pulled back at about 12"/minute at a 180° angle from the film. As the tab peeled off, the film delaminated and the reading on the dial was recorded.

55

2. Instron Tensile Tester: This was tested according to ASTM D 3759-79. A specimen of the delaminating film of this invention, not more than 2" in width was clamped in the grips of an Instron Tensile

Tester, taking care to align the long axis of the specimen with an imaginary line running between the points of attachment of the grips and including the center of the grips. No more tension was applied during clamping than was necessary to remove slack. The crosshead was set in motion at about 2"/minute and F-1, F-3, breakstrength, % elongation at break were recorded. (F-1 values are defined as force required to stretch the specimen 1%).

3. Light Transmittance Test: A model Aux-10 Gardner Pivotal-Sphere Hazemeter was used for this test. The hazemeter was first turned on and allowed to warm up for 15 minutes. Source "A" was selected for CIE illuminator. With no specimen in place and with light trap in the rear position, the digital read out was set to zero ( $T_3$  value) using the zero adjustment. The pivot sphere was then moved forward and the digital read out was then set to 100.0 ( $T_1$  value) using the calibrator control. A film specimen of about 1" x 1" was then put in the specimen holder the % transmittance or optical clarity ( $T_2$  value) was recorded. The sphere was pivoted backwards and a second reading ( $T_4$  value) was also recorded. % haze was calculated from the following formula:  $T_4/T_2 \times 100 = \% \text{ haze}$ .

The present invention has now been described with reference to several embodiments thereof. It will be apparent to those skilled in the art that many changes can be made in the embodiments described without departing from the scope of the present invention. Thus, the scope of the present invention should not be limited to the structures described in this application, but only by structures described by the language of the claims and the equivalents of those structures.

## Claims

1. A light transmissive film derived from a composition comprising 50 to 85 parts per weight of a first copolymer comprising at least one moiety derived from at least one olefinic monomeric unit and 50 to 15 parts by weight of a second copolymer comprising at least one moiety derived from at least one vinyl alcohol monomeric unit and said second copolymer being sufficiently incompatible with said first copolymer to form two phases within said film, one of said phases being continuous.

2. The film of claim 1, wherein said first copolymer comprises at least 90 pbw propylene monomeric units.

3. The film of claim 2, wherein said first copolymer comprises about 97 pbw propylene monomeric units and from about 2.2 pbw to about 2.7 pbw ethylene monomeric units.

4. The film of any one of claims 1 to 3, wherein said first copolymer further comprises from 0 to 15 pbw of monomeric units from a polar copolymerizable monomer substantially free of hydroxy (-OH) groups.

5. The film of claim 4, wherein said monomer is selected from acrylic acid, acrylonitrile, bicyclo [2,2,1] hept-2-ene, bis (B-chloroethyl) vinylphosphonate, carbon monoxide, diethyl fumarate, diethyl maleate, ethyl acrylate, methacrylic acid, N-methyl-N-vinylacetamide, styrene, vinyl acetate, vinyl chloride, and vinyl fluoride.

6. The film of claim 5, wherein the monomeric units are selected from acrylic acid, methacrylic acid and vinyl acetate.

7. The film of any one of claims 1 to 3, wherein said second copolymer is a copolymer containing monomeric units of hydrolyzed ethylene vinyl acetate.

8. The film of claim 7, wherein said second copolymer is ethylene vinyl alcohol.

9. A tamper indicating tape for securing a first container part to a second container part to enclose an opening in the container, comprising:

(a) a light transmissive film according to any one of claims 1 to 8 having a first major surface and an opposing second major surface;

(b) first colored indicia printed on said first major surface of said film;

(c) second colored indicia printed on said second major surface of said film, said first and second indicia having contrasting colors; and

(d) means for adhering said film to the first and the second container parts with a bond strength greater than the delamination force of said film, said adhesive means being coated on said first major surface of said film opposite said second indicia with a color substantially identical with said second indicia, whereby said second indicia are obscured when viewed against said adhesive means through said second major surface of said film;

(e) whereby when said film delaminates, the film becomes opaque so that said first indicia are obscured when viewed through said delamination opaque film, but said second indicia are perceptible over said delaminated opaque film to indicate separation of the container parts.

10. The tamper indicating tape of claim 9, wherein said adhesive means includes:

(a) a first layer of adhesive coated on said first major surface of said film opposite said second indicia for adhering said film to the first container part, said first layer of adhesive having a color substantially identical to said second indicia whereby said second indicia are obscured by said first layer of adhesive when viewed through said second major surface of said film; and

5 (b) a second layer of adhesive coated on said second major surface of said film for adhering said film to the second container part, said second layer of adhesive being colorless and light transmissive so that said first indicia are visible through said film and said second layer of adhesive;

(c) whereby when the first and the second container parts are separated, said film delaminates with said first layer of adhesive and a portion of said delaminated film remaining on the first container part, and  
10 said second layer of adhesive and the remaining portion of said delaminated film remaining on the second container part, and said delaminated film becomes opaque so that said first indicia are obscured when viewed through said delaminated film, but said second indicia are perceptible on said delaminated opacified film to indicate separation of the container parts.

11. The tamper indicating tape of either of claims 9 and 10, wherein said adhesive means includes a  
15 pressure sensitive adhesive layer coated on at least one major surface of said film.

12. In combination:

(a) a container having a first container part and a second container part for enclosing an opening in said container when secured together; and

(b) a tamper indicating tape for adhesively securing said first and said second container parts  
20 together to enclose said opening in said container, including a light transmissive film according to any one of claims 1 to 9 having a first major surface and an opposing second major surface,

first colored indicia printed on said first major surface of said film,  
second colored indicia printed on said second major surface of said film, said first and second indicia  
25 having contrasting colors, and

adhesive means for adhering said film to said first and said second container parts with a bond strength greater than the delamination force of said film, said adhesive means being coated on said first major surface of said film opposite said second indicia with a color substantially identical with said second indicia whereby said second indicia are obscured when viewed against said adhesive means through said second  
30 major surface of said film,

(c) whereby when said film is delaminated, said film becomes opaque so that said first indicia are obscured when viewed through said delaminated film, but said second indicia are perceptible over said delaminated opaque film to indicate separation of said container parts.





35

40

45

50

55






Fig. 3A




Fig. 3B




Fig. 4



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



Publication number: **0 349 160 A3**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: 89306056.6

(22) Date of filing: 15.06.89

(51) Int. Cl.<sup>5</sup>: C08L 23/02, B65D 55/06,  
C09J 7/02, G09F 3/02,  
C09F 3/02

(30) Priority: 27.06.88 US 212412

(43) Date of publication of application:  
03.01.90 Bulletin 90/01

(84) Designated Contracting States:  
CH DE FR GB IT LI

(88) Date of deferred publication of the search report:  
05.02.92 Bulletin 92/06

(71) Applicant: MINNESOTA MINING AND  
MANUFACTURING COMPANY  
3M Center, P.O. Box 33427  
St. Paul, Minnesota 55133-3427(US)

(72) Inventor: Rivera, Raymond R. c/o Minnesota  
Mining and  
Manufacturing Company 2501 Hudson Road  
St. Paul Minnesota 55144-1000(US)  
Inventor: VanVleet, Stephen B. c/o Minnesota  
Mining and  
Manufacturing Company 2501 Hudson Road  
St. Paul Minnesota 55144-1000(US)  
Inventor: Wilson, Shari J. c/o Minnesota  
Mining and  
Manufacturing Company 2501 Hudson Road  
St. Paul Minnesota 55144-1000(US)

(74) Representative: Baillie, Iain Cameron et al  
c/o Ladas & Parry, Altheimer Eck 2  
W-8000 München 2(DE)


(54) Tamper indicating tape and delaminating film therefore.

(57) The present invention relates to delaminating film and a tamper indicating tape made from same for use with a package to indicate opening of the package.

Delaminating films typically include two or more layers of polymeric materials, bonded together either by heat lamination, by coextrusion, or by means of an adhesive layer. Delamination of these composite films by separation of the various layers from each other provides indication of tampering. However, lamination or coextrusion of multiple polymeric layers increases the material expense of the film and tape and requires complex manufacturing techniques.

The present invention provides a tamper indicating film and tape for use with a package. The tape includes a delaminating film including phase separated polymers. Indicia are applied to opposing major surfaces of the film to indicate different conditions of the tape. The film is adhesively applied to secure container parts together and enclose an opening in the container. When applied, only one of

delaminated, one set of indicia is obscured and the other set of indicia is rendered perceptible.





European  
Patent Office

## EUROPEAN SEARCH REPORT

Application Number

EP 89 30 6056

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 041 747 (STAMICARBON) * page 2, line 1 - line 28 **	1-8	C 08 L 23/02 B 65 D 55/06 C 09 J 7/02 G 09 F 3/02 C 09 F 3/02
A,D	WO-A-8 603 472 (MINNESOTA MINING AND MANUFACTURING) * page 2, line 22 - page 4, line 24 **	9-12	
A	US-A-4 343 851 (N. SHEPTAK)Abstract	9-12	
A	US-A-4 539 263 (G. L. HOH)Abstract	9-12	
A	EP-A-0 148 030 (MINNESOTA MINING AND MANUFACTURING) * claim 1 **	9-12	
A	US-A-4 184 701 (P. S. FRANKLIN)Abstract	9-12	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 08 L B 65 D C 09 F C 08 J
The present search report has been drawn up for all claims			
Place of search		Date of completion of search	Examiner
The Hague		04 December 91	GOOVAERTS R.E.
CATEGORY OF CITED DOCUMENTS			
X: particularly relevant if taken alone		E: earlier patent document, but published on, or after the filing date	
Y: particularly relevant if combined with another document of the same category		D: document cited in the application	
A: technological background		L: document cited for other reasons	
O: non-written disclosure		&: member of the same patent family, corresponding	

BEST AVAILABLE COPY